# VABER INDUSTRIALE S.P.A.



PRODUZIONE ADESIVI E PRODOTTI CHIMICI INDUSTRIALI

Strada San Mauro, 203 I – 10156 Torino (ITALY) Tel. +39 011273.44.32 Fax +39 011273.17.76 /+39 011 223.77.72 e-mail: info@vaber.it

## **TECHNICAL DATA SHEET**

# VABER COLOR MASK

Date of release: 30.05.2005 Revision n°: 00 date: 18.11.2011 Approval: R&D Verified: QMS

## 1. GENERAL DESCRIPTION

VABER COLOR MASK is a polyethylene coextruded film for masking vehicles while operating with paints.

VABER COLOR MASK is electrostatic so fumes and paint are perfectly captured by the film leaving the environment clean.

VABER COLOR MASK shows excellent resistance to high temperatures and is therefore recommended for use with Infrared lamps.

#### 2. CHEMICAL AND PHYSICAL PROPERTIES

BASE	Polyethyelene coextruded film	
TENSILE STRENGTH AT BREAK	1,8 N/cm	
ELONGATION AT BREAK	50%	
THICKNESS	10 μm	

#### 3. INSTRUCTIONS FOR USE

Apply COLOR MASK on clean, dry, dust and oli free surfaces

#### 4. PACKAGING

COLOR MASK is available in rolls 4 x 150 mt

# 5. **US AGE, STORAGE AND SHELFLIFE**

COLOR MASK stored in its original container, in a dry and well ventilated area, at temperatures between 5°C and 30°C has a shelflife of 12months from manufacturing date.

## 6. DISCLAIMER

The above information and our technical indications (both verbal and written or resulting from testing), in particular those that regard the applications and uses of our products, correspond to our best knowledge and experience; however, they do not constitute our warranty relative to final results or our responsibility deriving from any juridical relationship whatsoever.

In fact, considering the multiplicity of materials, supports, handling and storage conditions, as well as the conditions of production and utilization, the user, in function of his specific circumstances of use, must always preventively verify all the information and instructions reported above.

No assertion contained in this publication is to be considered authorization or suggestion to violate any industrial property rights of third parties.