

# VABER INDUSTRIALE S.P.A.

PRODUZIONE ADESIVI E PRODOTTI CHIMICI INDUSTRIALI

Strada San Mauro, 203 I – 10156 Torino (ITALY)

Tel. +39 011273.44.32

Fax +39 011273.17.76 / +39 011 223.77.72

e-mail: info@vaber.it

## TECHNICAL DATA SHEET

**N° 3559805E**

**VABER PROTEX SPRAY**

**Date of release:** May 21, 1998

**Revision n°:** 4 **date:** June 28, 2002

**Compiler:** Cecconello

**T.D.:** Girivetto

**Q.M.S.:** Favatà

### 1. DESCRIPTION

VABER PROTEX SPRAY is a waxy protective product, especially used as a rust inhibitor for boxed areas.

Thanks to its capillarity guarantees a valid protection from rust, even on jointed areas.

VABER PROTEX SPRAY is employed for the protection, for long period, of surfaces of difficult application in machinery and big dimensions tooling.

### 2. CHEMICAL AND PHYSICAL CHARACTERISTICS

COLOUR AVAILABLE	: dark and transparent	
ODOUR	: slight, mineral	
PHYSIC STATE	: under-pressure liquid	
FLASH POINT	: <1°C	
DRY CONTENT (1 h @ 110°C)	: 20% ÷ 25%	1*
FILM	: waxy	
MEDIUM THICKNESS OF THE WET FILM		
SUGGESTED FOR SPRAY APPLICATION	: 100 µ	
HIDING POWER	: 3 m <sup>2</sup> /l	
SALT SPRAY CORROSION TEST	: > 500 h	2*

1\* VABER Method T-05 (ref. ASTM D 2369-95)

2\* VABER Method T-34 (ref. ASTM B117-73)

### **3. APPLICATION AND USE**

Shake well before the use.

Degrease the surfaces to be treated with anti-silicone product, and spray VABER PROTEX SPRAY. □

Remove from the paint with aliphatic solvents or ethylic alcohol eventual residuals.

### **4. SPECIAL INSTRUCTIONS**

VABER PROTEX SPRAY is into an under-pressure container.

Protect from sun rays and avoid temperature upper to +50°C.

Contains highly flammable liquid gas.

### **5. PACKING**

VABER PROTEX SPRAY is available in 600 ml spray container.

12 pieces/box.

### **6. STORAGE AND SHELF-LIFE**

VABER PROTEX SPRAY stored in its original package, in a well-ventilated place, under dry conditions, at temperature between +5°C and +35°C has a shelf-life of 12 months from the manufacturing date.

### **7. NOTICE**

The above information and our technical indications (both verbal and written or resulting from testing), in particular those that regard the applications and uses of our products, correspond to our best knowledge and experience; however, they do not constitute our warranty relative to final results or our responsibility deriving from any juridical relationship whatsoever.

In fact, considering the multiplicity of materials, supports, handling and storage conditions, as well as the conditions of production and utilization, the user, in function of his specific circumstances of use, must always preventively verify all the information and instructions reported above.

No assertion contained in this publication is to be considered authorization or suggestion to violate any industrial property rights of third parties.