



VABER INDUSTRIALE S.P.A.

Strada San Mauro, 203 I – 10156 Torino (ITALY)

Tel. +39 011273.44.32

Fax +39 011273.17.76 /+39 011 223.77.72

e-mail: info@vaber.it

STOP WATER STRIP

Date of release: July 5, 1993

Revision nr.: 7 date: 27.01.2010

Approval : R&D

Verified: QMS

1. DESCRIPTION

VABER SWS - STOP WATER STRIP is a butyl adhesive tape recommended for sealing different materials such as degreased metal (primed and galvanized), glass, wood, plastic, ceramic from moisture, water and dust.

VABER SWS - STOP WATER STRIP works in a wide range of temperatures while remaining flexible at low temperatures and maintains good cohesive properties at high temperatures.

2. CHEMICAL AND PHYSICAL CHARACTERISTICS

BASE	: butyl compound	
COLOUR	: black	
DENSITY	: $1,70 \pm 0,10 \text{ g/cm}^3$	1*
CONE PENETRATION	: from 65 to 75 dmm	2*
PEEL RESISTANCE	: $\geq 6 \text{ N/cm}$	3*
VAPOUR TRANSMISSION	: aprox 4g/m^2 in 24 hours	4*
WATER ABSORPTION	: 0,007%	5*
SERVICE TEMPERATURE		
Continuous	: from -40°C to $+110^\circ\text{C}$	
Max 4 hours	: up to 140°C	
APPLICATION TEMPERATURE	: from $+5^\circ\text{C}$ to $+40^\circ\text{C}$	

1* VABER method T-03 (ref. ASTM D792-91)

2* VABER method T-12 (ref. ASTM D 217-94) 150gr weight

3* VABER method T- 32 on steel

Follows technical sheet VABER SWS - Stop Water Strip
revision n°7 date: 27.01.2010

4* method NFT 300018

5* VABER method T-23 (ref ASTM D570) after 168hr water immersion at 23°C

3. INSTRUCTIONS FOR USE

VABER SWS STOP WATER STRIP must be applied on clean, dust free surfaces.

After positioning of the strip apply a homogeneous pressure on the whole surface to eliminate air entrapment

4. STORAGE AND SHELF LIFE

VABER SWS STOP WATER STRIP stored in its original package, in a well-ventilated place, under dry conditions, at temperature between +5°C and +25°C has a shelf life of 12 months from the manufacturing date.

5 NOTICE

The above information and our technical indications (both verbal and written or resulting from testing), in particular those that regard the applications and uses of our products, correspond to our best knowledge and experience; however, they do not constitute our warranty relative to final results or our responsibility deriving from any juridical relationship whatsoever.

In fact, considering the multiplicity of materials, supports, handling and storage conditions, as well as the conditions of production and utilization, the user, in function of his specific circumstances of use, must always preventively verify all the information and instructions reported above.

No assertion contained in this publication is to be considered authorization or suggestion to violate any industrial property rights of third parties.

©